



PINNACLE® PROTECTIVE COATINGS SYSTEM SELECTOR

TABLE OF CONTENTS

Steel	Page 2
Galvanized/Aluminum	Page 3
Concrete/Masonry (Previously Coated)	Page 3
Concrete/Poured (New/Uncoated)	Page 4
Concrete/Porous Block (New/Uncoated)	Page 4
Fleet Transportation	Page 5
Floors	Page 5
Interior Steel Barjoist and Metal Decking	Page 5
Summary of Surface Preparation	Page 6
Product Index	Page 7

SYSTEM SELECTOR

Pinnacle® Protective Coatings



How to use: To select the proper coatings system, select the substrate which best represents your situation. Select the system for your environment, then select your desired finish. Review the system features to find the protective coating system which is most suited for your exposure. For complete information, consult the technical data sheet found in the Pinnacle® Protective Coatings specification guide.

SUBSTRATE	SYSTEM TYPE	PRIMER COAT	FINISH COAT	FINISH	SURFACE PREP	SYSTEM FEATURES
STEEL						
●	Epoxy/Epoxy	Multi-E-Poxy® 180	Multi-E-Poxy® 180	Semi-Gloss	SP-1 & SP-2 or SP-3 or SP-6	Self-priming 1 or 2 coat application over most existing coatings. Tolerant to tight rust. Excellent resistance to moisture and chemicals.
●	Epoxy/Epoxy	Multi-E-Poxy® 180	Multi-E-Poxy® 240	Gloss	SP-1 & SP-2 or SP-3 or SP-6	System offers excellent resistance to moisture and chemicals. Surface tolerant to tight rust.
●	Epoxy/Epoxy	Multi-E-Prime 500	Multi-E-Poxy® 240	Gloss	SP-1 & SP-6	System offers excellent resistance to moisture and chemicals.
● ¹	Epoxy/Urethane	Multi-E-Poxy® 180	Multi-Thane 330	Gloss	SP-1 & SP-2, SP-3 or SP-6	System offers excellent color and gloss retention. Provides superior chemical and abrasion resistance. Surface tolerant to tight rust.
● ¹	Epoxy/Urethane	Multi-E-Prime 500	Multi-Thane 330	Gloss	SP-1 & SP-6	Excellent color and gloss retention. Superior chemical and abrasion resistance.
■	Epoxy/Acrylic Epoxy	Multi-E-Prime 500	Vers-E-Poxy 131	Gloss/Semi-Gloss	SP-1 & SP-6	Superior hi-build system which offers good moisture and chemical resistance.
■ ¹	Epoxy/Acrylic	Multi-E-Poxy® 180	Vers-Acryl 222	Semi-Gloss	SP-1 & SP-2 or SP-3	System offers high performance in moderate environments. Great color and gloss retention.
■ ¹	Epoxy/Acrylic	Multi-E-Prime 500	Vers-Acryl 222	Semi-Gloss	SP-1 & SP-6	Superior hi-build system. Excellent flexibility, color and gloss retention.
● ¹	Zinc/Urethane	Endura-Zinc 768	Multi-Thane 330	Gloss	SP-1 and SP-6	Provides greatest level of corrosion resistance. Excellent color and gloss retention. Provides superior chemical and abrasion resistance.
■ ¹	Zinc/Urethane	1st ct Endura-Zinc 705 2nd ct Multi-E-Prime 500	Multi-Thane 330	Gloss	SP-1 & SP-6	Provides cathodic protection with superior chemical and abrasion resistance. Excellent color and gloss retention.
▲	Alkyd/Alkyd	Iron Prime 600	CoteALL® Enamel	Gloss	SP-1 & SP-6	User friendly for in-house maintenance. Variety of colors in primers and finishes. Good color and gloss retention.
▲	Alkyd/Alkyd	CoteALL® Primer	CoteALL® Enamel	Gloss	SP-1 & SP-6	User friendly for in-house maintenance. Variety of colors in primers and finishes. Good color and gloss retention.
▲	Silicone Alkyd/ Silicone Alkyd	AZ-2402 CoteALL® High Heat Aluminum	AZ-2402 CoteALL® High Heat Aluminum	Low Gloss	SP-1 & SP-10	Resists temperatures up to 1200° F, Interior or exterior exposure. Bright Aluminum color.
▲ ¹	Alkyd/Acrylic	Iron Prime 600	Vers-Acryl 222	Semi-Gloss	SP-1 & SP-6	User friendly for in-house maintenance. Variety of colors in primers and finishes. Offers excellent color and gloss retention.
▲ ¹	Alkyd/Acrylic	CoteALL® Primer	Vers-Acryl 222	Semi-Gloss	SP-1 & SP-6	User friendly for in-house maintenance. Variety of colors in primers and finishes. Offers excellent color and gloss retention.
▲ ¹	Acrylic/Acrylic	Vers-Acryl 200	Vers-Acryl 222	Semi-Gloss	SP-1 & SP-6	Environmentally friendly system for in-house maintenance. Variety of colors in primers and finishes. Excellent flexibility, color and gloss retention.

STEEL - WATER IMMERSION (Non-Potable)

●	Epoxy/Epoxy	Multi-E-Poxy® 180	Multi-E-Poxy® 180	Semi-Gloss	SP-1 & SP-10	Excellent performance in immersion service (non-potable freshwater). Performs well in some chemical solutions in immersion conditions.
---	-------------	-------------------	-------------------	------------	--------------	--

● Severe Environments: Frequent fumes and spillage of strong chemicals including acids, alkalis and solvents. Constant high humidity and moisture conditions. Frequent chemical cleaning.
 ■ Moderate Environments: Frequent fumes and spillage of mild chemicals. Intermittent humidity and moisture, mold and mildew conditions. Occasional chemical cleaning.
 ▲ Outdoor weathering and/or mild industrial fumes, normal humidity.
 1 In addition to being a good system for the above noted environment, it also exhibits excellent gloss and color retention when exposed to outdoor weather conditions.

SYSTEM SELECTOR

Pinnacle® Protective Coatings



SUBSTRATE	SYSTEM TYPE	PRIMER COAT	FINISH COAT	FINISH	SURFACE PREP	SYSTEM FEATURES
GALVANIZED/ALUMINUM						
●	Epoxy/Epoxy	Mult-E-Poxy® 180	Mult-E-Poxy® 180	Semi-Gloss	SP-1 & SP-2, SP-3 or SP-7	Self-priming 1 or 2 coat application over most existing coatings. Tolerant to tight rust. Excellent resistance to moisture and chemicals.
●	Epoxy/Epoxy	Mult-E-Poxy® 180	Mult-E-Poxy® 240	Gloss	SP-1 & SP-2, SP-3 or SP-7	System offers excellent resistance to moisture and chemicals. Surface tolerant to tight rust.
●	Epoxy/Epoxy	Mult-E-Prime 500	Mult-E-Poxy® 240	Gloss	SP-1 & SP-2, SP-3 or SP-7	System offers excellent adhesion. Excellent moisture and chemical resistance.
● ¹	Epoxy/Urethane	Mult-E-Poxy® 180	Multi-Thane 330	Gloss	SP-1 & SP-2, SP-3 or SP-7	Excellent color and gloss retention. Provides superior chemical and abrasion resistance. Offers good moisture resistance.
● ¹	Epoxy/Urethane	Mult-E-Prime 500	Multi-Thane 330	Gloss	SP-1 & SP-2, SP-3 or SP-7	System offers excellent color and gloss retention. Provides superior chemical and abrasion resistance.
■ ¹	Epoxy/Acrylic	Mult-E-Poxy® 180	Vers-Acryl 222	Semi-Gloss	SP-1 & SP-2 or SP-3	System offers high performance in moderate environments. Excellent color and gloss retention.
■ ¹	Epoxy/Acrylic	Mult-E-Prime 500	Vers-Acryl 222	Semi-Gloss	SP-1 & SP-2 or SP-3	Superior hi-build system. Excellent flexibility, color and gloss retention.
■ ¹	Zinc/Zinc	Endura-Zinc 703	Endura-Zinc 703	Semi-Gloss	SP-1 & SP-2 or SP-3	Rust inhibitive metallic zinc coating system with excellent adhesion. Gives the appearance of a new galvanized finish.
■ ¹	Zinc/Acrylic	Endura-Zinc 700	Vers-Acryl 222	Semi-Gloss	SP-1 & SP-2 or SP-3	Surface tolerant to rusted galvanized. Provides galvanic protection. Excellent gloss and color retention.
▲	Alkyd/Alkyd	Iron Prime 600	CoteALL® Enamel	Gloss	SP-1 & SP-2 or SP-3	User friendly for in-house maintenance. Variety of colors in primers and finishes. Good color and gloss retention.
▲ ¹	Alkyd/Acrylic	Iron Prime 600	Vers-Acryl 222	Semi-Gloss	SP-1 & SP-2 or SP-3	User friendly for in-house maintenance. Variety of colors in primers and finishes. Offers excellent color and gloss retention.
▲	Acrylic/Acrylic Epoxy	Vers-Acryl 200	Vers-E-Poxy 131	Gloss/Semi-Gloss	SP-1 & SP-2 or SP-3	Environmentally friendly system with good flexibility, moisture and chemical resistance.
▲ ¹	Acrylic/Acrylic	Vers-Acryl 200	Vers-Acryl 222	Semi-Gloss	SP-1 & SP-2 or SP-3	Environmentally friendly system for in-house maintenance. Excellent flexibility, color and gloss retention.

SUBSTRATE	SYSTEM TYPE	PRIMER COAT	FINISH COAT	FINISH	SURFACE PREP	SYSTEM FEATURES
CONCRETE/MASONRY (Previously Coated)						
●	Epoxy/Epoxy	Mult-E-Poxy® 180	Mult-E-Poxy® 180	Semi-Gloss	Clean & Abrade or Acid Etch	Self-priming and surface tolerant over most existing coatings. Excellent resistance to moisture and chemicals.
●	Epoxy/Epoxy	Mult-E-Poxy® 180	Muti-E-Poxy® 240	Gloss	Clean & Abrade or Acid Etch	System offers excellent resistance to moisture and chemicals. Surface tolerant over most existing coatings.
● ¹	Epoxy/Urethane	Mult-E-Poxy® 180	Multi-Thane 330	Gloss	Clean & Abrade or Acid Etch	System offers excellent color and gloss retention. Provides superior chemical and abrasion resistance.
■ ¹	Epoxy/Acrylic	Mult-E-Poxy® 180	Vers-Acryl 222	Semi-Gloss	Clean & Abrade or Acid Etch	System offers high performance in moderate environments. Great color and gloss retention.
■	Acrylic/Acrylic Epoxy	Vers-Acryl 200	Vers-E-Poxy 131	Gloss/Semi-Gloss	Clean & Abrade or Acid Etch	Environmentally friendly system with good flexibility, moisture and chemical resistance.
▲ ¹	Acrylic/Acrylic	Vers-Acryl 200	Vers-Acryl 222	Semi-Gloss	Clean & Abrade or Acid Etch	Environmentally friendly system for in-house maintenance. Excellent flexibility, color and gloss retention.

● Severe Environments: Frequent fumes and spillage of strong chemicals including acids, alkalis and solvents. Constant high humidity and moisture conditions. Frequent chemical cleaning.

■ Moderate Environments: Frequent fumes and spillage of mild chemicals. Intermittent humidity and moisture, mold and mildew conditions. Occasional chemical cleaning.

▲ Outdoor weathering and/or mild industrial fumes, normal humidity.

¹ In addition to being a good system for the above noted environment, it also exhibits excellent gloss and color retention when exposed to outdoor weather conditions.

SYSTEM SELECTOR

Pinnacle® Protective Coatings



SUBSTRATE	SYSTEM TYPE	PRIMER COAT	FINISH COAT	FINISH	SURFACE PREP	SYSTEM FEATURES
CONCRETE/POURED (New/Uncoated)						
●	Epoxy/Epoxy	Multi-E-Poxy® 180	Multi-E-Poxy® 180	Semi-Gloss	Clean & Abrade or Acid Etch	Self-priming system with excellent resistance to moisture and chemicals.
●	Epoxy/Epoxy	Multi-E-Poxy® 180	Multi-E-Poxy® 240	Gloss	Clean & Abrade or Acid Etch	System offers excellent resistance to moisture and chemicals.
● ¹	Epoxy/Urethane	Multi-E-Poxy® 180	Multi-Thane 330	Gloss	Clean & Abrade or Acid Etch	System offers excellent color and gloss retention. Superior chemical and abrasion resistance.
■ ¹	Epoxy/Acrylic	Multi-E-Poxy® 180	Vers-Acryl 222	Semi-Gloss	Clean & Abrade or Acid Etch	System offers high performance in moderate environments. Great color and gloss retention.
■	Acrylic/Acrylic Epoxy	Vers-Acryl 200	Vers-E-Poxy 131	Gloss/Semi-Gloss	Clean & Abrade or Acid Etch	Environmentally friendly system with good flexibility, and moisture and chemical resistance.
▲ ¹	Acrylic/Acrylic	Vers-Acryl 200	Vers-Acryl 222	Semi-Gloss	Clean & Abrade or Acid Etch	Environmentally friendly system for in-house maintenance. Excellent flexibility, color and gloss retention.

CONCRETE/WATER IMMERSION (Non-Potable)						
●	Epoxy/Epoxy	Multi-E-Poxy® 180	Multi-E-Poxy® 180	Semi-Gloss	Acid Etch or Abrasive Blast	Excellent performance in immersion service (non-potable freshwater). Performs well in some chemical solutions in immersion conditions.

SUBSTRATE	SYSTEM TYPE	PRIMER COAT	FINISH COAT	FINISH	SURFACE PREP	SYSTEM FEATURES
CONCRETE/POROUS BLOCK (New/Uncoated)						
●	Epoxy/Epoxy	Multi-E-Poxy® 180	Multi-E-Poxy® 180	Semi-Gloss	Clean & Abrade or Acid Etch	Self-priming system with excellent resistance to moisture and chemicals.
●	Epoxy/Epoxy	Multi-E-Poxy® 180	Multi-E-Poxy® 240	Gloss	Clean & Abrade or Acid Etch	System offers excellent resistance to moisture and chemicals.
● ¹	Epoxy/Urethane	Multi-E-Poxy® 180	Multi-Thane 330	Gloss	Clean & Abrade or Acid Etch	System offers color and gloss retention. Superior chemical and abrasion resistance.
●	Epoxy Block Filler/Epoxy	Vers-E-Poxy 100	Multi-E-Poxy® 180	Semi-Gloss	Clean & Abrade or Acid Etch	Excellent hi-build, moisture resistant system. Develops a smooth finish on rough, porous surfaces.
■	Epoxy Block Filler/Epoxy	Vers-E-Poxy 100	Vers-E-Poxy 131	Gloss/Semi-Gloss	Clean & Abrade or Acid Etch	Environmentally friendly system that exhibits good flexibility, moisture and chemical resistance. Also provides good color and gloss retention. Develops a smooth finish on rough, porous surfaces.
● ¹	Epoxy Block Filler/Urethane	Vers-E-Poxy 100	Multi-Thane 330	Gloss	Clean & Abrade or Acid Etch	Excellent hi-build, moisture resistant system. Excellent gloss and color resistance. Develops a smooth finish on rough, porous surfaces.
■	Acrylic Block Filler/Epoxy	Permafil	Vers-E-Poxy 131	Gloss/Semi-Gloss	Clean & Abrade or Acid Etch	Environmentally friendly system that exhibits good moisture and chemical resistance. Excellent flexibility, color and gloss.
■ ¹	Acrylic Block Filler/Acrylic	Permafil	Vers-Acryl 222	Semi-Gloss	Clean & Abrade or Acid Etch	Environmentally friendly system that exhibits good flexibility, moisture and chemical resistance.
■	Rubber/Rubber	V-Tech® 801	V-Tech® 801	Flat	Clean & Abrade or Acid Etch	A rubberized masonry system designed to give exceptional durability, alkali and moisture resistance.

● Severe Environments: Frequent fumes and spillage of strong chemicals including acids, alkalis and solvents. Constant high humidity and moisture conditions. Frequent chemical cleaning.
 ▲ Moderate Environments: Frequent fumes and spillage of mild chemicals. Intermittent humidity and moisture, mold and mildew conditions. Occasional chemical cleaning.
 ▲ Outdoor weathering and/or mild industrial fumes, normal humidity.
 1 In addition to being a good system for the above noted environment, it also exhibits excellent gloss and color retention when exposed to outdoor weather conditions.

SYSTEM SELECTOR

Pinnacle® Protective Coatings



SUBSTRATE	SYSTEM TYPE	PRIMER COAT	FINISH COAT	FINISH	SURFACE PREP	SYSTEM FEATURES
FLEET TRANSPORTATION (Weather Protection, Road Salt, Grime and Chemicals)						
● ¹	Epoxy/Urethane	Multi-E-Poxy® 180	Multi-Thane 330	Gloss	SP-1 and SP-6	Excellent hi-build characteristics. Superior abrasion resistance. Excellent color and gloss retention.
● ¹	Urethane/Urethane	Stratum® Primer	Multi-Thane 330	Gloss	SP-1 and SP-6	Maximum chip and abrasion resistance. High gloss finish. Variety of colors in primers and finishes. Superior chemical resistance. Excellent color and gloss retention.
● ¹	Urethane/Urethane	Stratum® Primer	PinnAcle® 460	Gloss	SP-1 and SP-6	Excellent chip resistant system that gives a "wet" look, high gloss finish. Variety of colors in primers and finishes. Superior chemical resistance. Excellent color and gloss retention.

SUBSTRATE	SYSTEM TYPE	PRIMER COAT	FINISH COAT	FINISH	SURFACE PREP	SYSTEM FEATURES
FLOORS (Concrete Floors exposed to Rubber-tired Vehicles and Foot Traffic as well as Moisture, Chemicals Spills and Chemical Cleaning.)						
●	Epoxy/Epoxy	Multi-E-Poxy® 180	Multi-E-Poxy® 180	Semi-Gloss	Clean & Abrade or Acid Etch	Self-priming system with excellent resistance to moisture and chemicals. Great adhesion properties.
●	Epoxy/Urethane	Multi-E-Poxy® 180	Multi-Thane 330	Gloss	Clean & Abrade or Acid Etch	Excellent adhesion with outstanding chemical and abrasion resistance. Excellent color and gloss retention.
■	Epoxy/Moisture Cure Urethane	Multi-E-Prime 505	Miracle Glaze	Gloss	Clean & Abrade or Acid Etch	System offers high performance for heavy foot and light rubber wheeled traffic areas. Not intended for wet environments or outdoor exposure.

SUBSTRATE	SYSTEM TYPE	PRIMER COAT	FINISH COAT	FINISH	SURFACE PREP	SYSTEM FEATURES
INTERIOR STEEL BARJOIST AND METAL DECKING (Dryfall System)						
▲	Latex		Luminance 300	Flat	SP2 and/or SP3 or SP7	A fast dry flat latex dri-mist finish exhibiting great fall out characteristics.
▲	Latex		Luminance 303	Semi-Gloss	SP2 and/or SP3 or SP7	A fast dry semi-gloss latex dri-mist finish exhibiting great fall out characteristics.
▲	Alkyd		Luminance 325	Flat	SP1, SP2 or SP3, or SP7	A fast dry flat alkyd dri-mist finish exhibiting great fall out characteristics.
▲	Alkyd		Luminance 350	Semi-Gloss	SP1, SP2 or SP3, or SP7	A fast dry semi-gloss alkyd dri-mist finish exhibiting great fall out characteristics.
▲	Alkyd		Luminance 355	Eggshell	SP1, SP2 or SP3, or SP7	A fast dry eggshell, low odor alkyd dri-mist finish exhibiting great fall out characteristics.

SUBSTRATE	SYSTEM TYPE	PRIMER COAT	FINISH COAT	FINISH	SURFACE PREP	SYSTEM FEATURES
GALVANIZED METAL (Dryfall System)						
▲	Latex		Luminance 300	Flat	SP2 or SP3 or SP7	A fast dry flat latex dri-mist finish exhibiting great fall out characteristics.
▲	Latex		Luminance 303	Semi-Gloss	SP2 or SP3 or SP7	A fast dry semi-gloss latex dri-mist finish exhibiting great fall out characteristics.

- Severe Environments: Frequent fumes and spillage of strong chemicals including acids, alkalis and solvents. Constant high humidity and moisture conditions. Frequent chemical cleaning.
- Moderate Environments: Frequent fumes and spillage of mild chemicals. Intermittent humidity and moisture, mold and mildew conditions. Occasional chemical cleaning.
- ▲ Outdoor weathering and/or mild industrial fumes, normal humidity.
- 1 In addition to being a good system for the above noted environment, it also exhibits excellent gloss and color retention when exposed to outdoor weather conditions.

SUMMARY OF SURFACE PREPARATION STEEL SURFACES

Steel should be cleaned by one or more of the following surface preparation methods described. These methods were originally established by the Society for Protective Coatings (formerly the Steel Structures Painting Council).

SP1: SSPC-SP 1 SOLVENT CLEANING

Solvent cleaning is used primarily to remove oil, grease, dirt, soil, drawing compounds and other similar organic compounds.

SP2: SSPC-SP 2 HAND TOOL CLEANING

A surface prepared with hand tools requires that all loose mill scale, loose rust, loose paint and other loose foreign material be removed. It is not intended to remove adherent mill scale, rust and paint. Material is considered to be adherent if they can not be removed by lifting with a dull putty knife.

SP3: SSPC-SP 3 POWER TOOL CLEANING

A surface prepared with power tools requires that all loose mill scale, loose rust, loose paint and other loose foreign material be removed. It is not intended to remove adherent mill scale, rust and paint or to produce a surface profile. Material is considered to be adherent if they can not be removed by lifting with a dull putty knife. Types of power tools used are generally impact or rotary power tools.

SP5: SSPC-SP 5 WHITE METAL BLAST CLEANING

Removal of all visible rust, mill scale, paint, and foreign matter by blast cleaning by wheel of nozzle (dry or wet) using sand, grit, or shot.

SP6: SSPC-SP 6 COMMERCIAL BLAST CLEANING

A surface prepared according to SSPC-SP-6-85 requires that the surface, when viewed, be free of all visible oil, grease, dirt, dust, mill scale, rust, paint, oxides, corrosion products and other foreign matter. Light staining due to rust, mill scale, and previous coatings may remain on no more than 33% of each square inch of surface area. The profile produced by blasting should be controlled by the selection of blast

media and should not exceed the filling capacity of the primer to be applied.

SP7: SSPC-SP 7 BRUSH-OFF BLAST CLEANING

A surface prepared according to SSPC-SP-7-85 requires that the surface, when viewed, be free of all visible oil, grease, dirt, dust, loose rust, loose mill scale, and loose coatings. It is not intended to remove tightly bonded mill scale, sound rust or adherent coatings. A Brush-off Blast may also be used to abrade a previous coating, providing a surface profile for new coating application.

SP8: SSPC-SP 8 PICKLING

Complete removal of rust and mill scale by acid pickling, duplex pickling, or electrolytic pickling.

SP10: SSPC-SP 10 NEAR-WHITE BLAST CLEANING

A surface prepared according to SSPC-SP-10-85 requires that the surface, when viewed, be free of all visible oil, grease, dirt, dust, mill scale, rust, paint, oxides, corrosion products and other foreign matter. Light staining due to rust, mill scale, and previous coatings may remain on no more than 5% of each square inch of surface area.

SP11: SSPC-SP-11 POWER TOOL CLEANING TO BARE METAL

Power Tool Cleaning to bare metal may be used to prepare the surface. The prepared surface will be free of all visible oil, grease, dirt, rust, paint, and other foreign matter. Residues of rust and paint may be left in the pits of the surface. This method may be used to produce a surface profile in small areas. Surface cleaning power tools are generally impact or profile producing power tools.

SUMMARY OF SURFACE PREPARATION GALVANIZED SURFACES

Galvanized metal is iron or steel with a 2 - 3 mil (DFT) coating of zinc metal. This process which is called Hot Dip Galvanizing is done at the fabrication mill. Galvanized steel normally comes from the mill chemically treated, or passivated, to prevent white rusting or oxidation of the galvanized surface during the time it is being stored or shipped to the project site.

PREPARING GALVANIZED METAL

The only two ways to prepare a passivated galvanized steel surface for painting is to thoroughly scrub with a phosphoric acid solution and thoroughly rinse with clean water or you can abrasive brush blast the new galvanized metal surface

removing the treatment.

Always apply a test patch of the coating to the galvanized surface to be painted to determine if you are getting proper adhesion.

SUMMARY OF SURFACE PREPARATION CONCRETE SURFACES

Scrape all loose, peeling and cracked paint off surfaces. Remove any paint that is not tightly adhering. Feather all edges of remaining paint film.

PREPARING A CONCRETE SLAB

Test for Curing Compound by applying a muriatic acid solution to bare concrete. If the solution does not react (bubble vigorously) when in contact with the concrete, the presence of a curing compound is indicated.

Test for Grease by pouring a small amount of water on the floor. If it beads up, oil and/or grease is present.

Test for Moisture by taping a 2' x 2' plastic sheet over different areas of the floor. Examine the plastic after 24 hours for signs of moisture.

Test Adhesion of Previous Coatings by cutting 2" x 2" "X" cross-hatches into remaining coatings. Then apply 6" stripes of duct tape over the "X's" and press the duct tape firmly onto the floor and then quickly pull it off. Examine the tape for removal of coatings.

DEGREASE A CONCRETE FLOOR by dampening the concrete surface and

then applying a suitable cleaner/degreaser. Allow to soak for 15 to 20 minutes. Keep the surface wet by adding water while scrubbing the solution over the entire floor. Rinse floor thoroughly.

PREPARING A CONCRETE FLOOR BY ACID ETCHING

Apply a 1:1 solution of muriatic acid and water through a sprinkling device. The acid should bubble vigorously when applied to the concrete. Allow reaction between solution and concrete to occur for approximately 3-5 minutes, then follow with a stiff broom or mechanical scrubber to remove surface laitance. Rinse the etched surface with clean water, preferably with a high pressure washer.

PREPARING A CONCRETE FLOOR BY SHOT BLASTING

Shot blast to produce a 3 - 4 mil profile on the concrete floor. The shot blasting machine must be equipped with a vacuum system to recover shot and to reduce airborne dust and contaminants.

Additional and expanded surface preparation information is available on the Diamond Vogel® website at www.diamondvogel.com. This information covers detailed preparations including full SSPC Specifications as well as products that have provided consistent results.

PROTECTIVE COATINGS INCLUDED IN THE PINNACLE® PROTECTIVE COATINGS SYSTEM SELECTOR

ALPHABETICAL PRODUCT NAME LISTING

Product Name	Product Number	Product Type	Tab Location
CoteALL® Aluminum	AZ-2401	Alkyd	Alkyd
CoteALL® Hi-Heat Aluminum	AZ-2402	Silicone Alkyd	Alkyd
CoteALL® Multi-Purpose Enamel	AZ-Series	Alkyd	Alkyd
CoteALL® Primer	AZ-Series	Alkyd	Alkyd
Endura-Zinc Metallic Zinc Dust Primer	PB-0411	Zinc	Zinc
Endura-Zinc 703 Brite Cold Galvanizing Finish	PB-2416	Zinc	Zinc
Endura-Zinc 705 Organic Zinc Rich Primer	PL-0512	Zinc	Zinc
Endura-Zinc 768 Zinc Rich Epoxy Primer	LF-0255	Zinc	Zinc
Iron Prime 600 Fast Dry Universal Primer	LU-Series	Alkyd	Alkyd
Luminance 300 Latex Dri-Mist Flat	MV-1518	Acrylic	Acrylic
Luminance 303 Latex Dri-Mist Semi-Gloss	MV-1520	Acrylic	Acrylic
Luminance 325 Alkyd Dri-Mist Flat	LB-1625	Alkyd	Alkyd
Luminance 350 Alkyd Dri-Mist Semi-Gloss	LB-1620	Alkyd	Alkyd
Luminance 355 Alkyd Dri-Mist Eggshell	LB-1604	Alkyd	Alkyd
Miracle Glaze	LG-0414	Polyurethane	Polyurethane
Multi-E-Poxy® 180	LG-Series	Epoxy	Epoxy
Multi-E-Poxy® 240	LF-1241	Epoxy	Epoxy
Multi-E-Prime 500 Hi-Build Epoxy Primer	LF-Series	Epoxy	Epoxy
Multi-E-Prime 505 Clear Epoxy Concrete Primer/Sealer	LF-0209	Epoxy	Epoxy
Multi-Thane 330 Gloss	IG-Series	Polyurethane	Polyurethane
Permafil Acrylic Block Filler	BF-1501	Acrylic	Latex
PinnAcle® 460	IG-Series	Polyurethane	Polyurethane
Stratum® Primer	PG-Series	Polyurethane	Polyurethane
Vers-Acryl 200 Acrylic Maintenance Primer/Finish	MC-1501	Acrylic	Latex
Vers-Acryl 222 Acrylic Maintenance Finish Semi-Gloss	MC-Series	Acrylic	Acrylic
Vers-E-Poxy 100 Acrylic Epoxy Block Filler	MC-1234	Acrylic Epoxy	Block Fillers
Vers-E-Poxy 131 Waterborne Acrylic Epoxy Finish	MC-Series	Epoxy	Epoxy
V-Tech® 801 Rubberized Masonry Coating	AF-1410	Rubber	Specialty Coatings

