



AU-1404

Prime-O-Seal

Exterior Alkyd Primer/Sealer

Product Data Sheet

PRODUCT DESCRIPTION

Prime-O-Seal is a solvent thinned, breather type alkyd resin coating designed to provide excellent adhesion and sealing of exterior **wood** surfaces.

TYPICAL USES

Formulated for use as an exterior primer/sealer coat on unprimed wood, chalky surfaces and old weathered surfaces. May be topcoated with both solvent and water thinned exterior finishes. Ideal for both residential and commercial applications.

BASES & COLORS (tintable with ACS colorant)

AU-1404 White 0-4 oz/gal

With the addition of ACS colorant, it can be shaded to approximate the color of the finish coat.

PHYSICAL PROPERTIES(AU-1404)

Resin Type	Alkyd
Clean-up Solvent	Mineral Spirits
Finish	0 – 5 @ 85°
Solids by Weight	75 %
Solids by Volume	56 %

Recommended Dry Film Thickness per Coat	1.5 – 2 mils
---	--------------

Wet Film to Achieve DFT	2.75 – 3.5 mils
-------------------------	-----------------

Theoretical Coverage @ 1 mil	898 ft ² /gallon
------------------------------	-----------------------------

Practical Coverage at Recommended DFT ¹	449 – 599 ft ² /gallon
--	-----------------------------------

<u>Dry Times</u> ² @ 70° F (21° C) and 50% R.H.	Touch 2 to 4 hours Recoat 12 hours
--	---------------------------------------

VOC's	345 grams/liter
-------	-----------------

1 Spread rates are estimates based on products volume solids and make no allowance for material loss during application. Actual spread rates may vary dependent on applicator experience, surface porosity and texture.

2 Dry times may vary depending upon temperature, humidity and degree of air movement.

SPECIFICATIONS

Exterior Wood

1 ct AU-1404 Exterior Alkyd Primer/Sealer
2 cts AS/AZ/CS-Series Alkyd Finish
or
2 cts B-Series Exterior Latex Finish

This product meets or exceeds Master Painters Institute (MPI) # 5 approval standards.

For more detailed recommendations, please contact your local Diamond Vogel Sales Representative.

SURFACE PREPARATION

All surfaces must be cured, clean, sound, dry and free of all dirt, dust, efflorescence, wax, oil, grease, chalk and any other contamination that would interfere with new coating adhesion. **Bare surfaces must be properly prepared prior to application of this product.**

Wood Surfaces: Patch nail holes, cracks and imperfections with exterior spackling compound. Sand and wipe clean. May be used on woods subject to tannin stains such as cedar and redwood.

Previously Painted Surfaces

- Power or hand washing is recommended to remove contamination. If oil or grease is present, use of a cleaner/degreaser is required. All cleaning residue must be completely rinsed from the surface. Allow to dry.
- Remove all loose coatings and corrosion by scraping, sanding or other abrading method. Dull glossy, slick and/or non-porous surfaces with sandpaper.
- Patch and fill areas as needed. Spot prime bare areas with appropriate primer.

Mildew

Remove by using a solution of one (1) part household bleach and three (3) parts water. Apply to mildewed area and scrub. Allow solution to remain on the surface for 3 to 5 minutes then rinse completely and allow to dry before coating application. Do not add detergents or ammonia to the bleach/water solution.

APPLICATION

- Stir material prior to application. Intermix tinted containers to ensure color uniformity of all material.
- Equipment must be clean prior to start. Flush airless lines with mineral spirits or turpentine.
- Apply by brush, roller or spray. A good quality synthetic brush will make application easier. Select a roller cover suited for the texture of the surface to be coated. Airless tip sizes of .013 to .015 are recommended.
- Apply the product in full even coats and maintain a wet edge.
- Do Not Thin

ENVIRONMENTAL VARIABLES

Minimum surface and air temperature required for application is 40° F (4° C) and at least 5° F (3° C) above the dew point. While this product is not subject to freezing, curing is affected by temperature, humidity and air movement; cold temperatures will greatly increase the dry time. Application at elevated temperatures, wind conditions, and/or low humidity may require special application procedures to achieve proper film formation.

CLEAN-UP

Clean up spills and equipment immediately with mineral spirits.

CAUTIONS

For exterior use only
Do not apply below 40° F
Not intended for use on floors
Do not take internally
Use with adequate ventilation
KEEP OUT OF REACH OF CHILDREN

*WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and wet mop. Before you start, find out how to protect yourself and your family by contacting the national Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Limited Warranty

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products. Since Diamond Vogel Paints does not control the application of its products, or the condition of the surfaces to which they are applied, Diamond Vogel Paint's liability will under no circumstances exceed replacement of the product.