



BH-Series

Weather-Plate

Exterior 100% Acrylic Latex Semi-Gloss

Product Data Sheet

PRODUCT DESCRIPTION

Weather Plate is a high quality exterior 100% acrylic latex that dries to a durable semi-gloss finish. The 100% acrylic technology provides excellent fade resistance which allows colors to remain beautiful for years.

TYPICAL USES

Formulated for use on residential and commercial exterior new or previously painted wood, hardboard, vinyl siding, cement board, aluminum, galvanized metal and masonry surfaces. Ideal for use on siding, gutters, soffits and foundations.

BASES & COLORS (tintable with ACS colorant)

BH-1540 White	N/A
BH-1541 White Base	0-4 oz/gal
BH-1542 Midtone Base	2-6 oz/gal
BH-1543 Deep Base	4-10 oz/gal
BH-0544 Neutral Base	4-14 oz/gal

PHYSICAL PROPERTIES (BH-1540)

Resin Type	100% Acrylic Latex
Clean-up Solvent	Water
Finish	30 – 40 @ 60°
Solids by Weight	45 %
Solids by Volume	34 %

Recommended Dry Film
Thickness per Coat 1.5 – 2 mils

Wet Film to Achieve DFT 4 – 5.5 mils

Theoretical Coverage
@ 1 mil 545 ft²/gallon

Practical Coverage at
Recommended DFT¹ 276 – 363 ft²/gallon

Dry Times²
@ 70° F (21° C) Touch ½ to 2 hours
and 50% R.H. Recoat 2 to 4 hours

VOC's 140 - 141 grams/liter

1 Spread rates are estimates based on products volume solids and make no allowance for material loss during application. Actual spread rates may vary dependent on applicator experience, surface porosity and texture.

2 Dry times may vary depending upon temperature, humidity and degree of air movement.

SPECIFICATIONS

Galvanized and Aluminum Metal

1 ct V-Cote 200 Acrylic Maintenance Primer
2 cts Weather Plate Semi-Gloss

Exterior Wood

1 ct AU-Series Alkyd Primer
or
1 ct BU-Series Acrylic Primer
2 cts Weather Plate Semi-Gloss

Ferrous Metal

1 ct AZ-Series Cote-All Universal Primer
2 cts Weather Plate Semi-Gloss

Block

Smooth
1 ct MC-0521 Masonry Conditioner
or
1 ct BU-Series Acrylic Latex Primer
2 cts Weather Plate Semi-Gloss

Porous
1 ct BF-Series Exterior Block Filler
2 cts Weather Plate Semi-Gloss

Poured Concrete

1 ct BU-Series Acrylic Latex Primer
2 cts Weather Plate Semi-Gloss

Cement Siding

Pre-primed
2 cts Weather Plate Semi-Gloss
Unprimed
1 ct BU-Series Acrylic Latex Primer
2 cts Weather Plate Semi-Gloss

Vinyl Siding

2 cts Weather Plate Semi-Gloss

For more detailed recommendations, please contact your local Diamond Vogel Sales Representative.

SURFACE PREPARATION

All surfaces must be cured, clean, sound, dry and free of all dirt, dust, efflorescence, wax, oil, grease, chalk and any other contamination that would interfere with new coating adhesion. **Bare surfaces must be properly prepared and primed prior to application of this product.**

Masonry Surfaces- Poured Concrete, Concrete Block:

New concrete and mortar should cure for a *minimum* of 30 days at 72° F (22° C) prior to coating application. Level all surface projections and mortar spatters by stoning. Rake mortar joints clean and remove all soluble salts.

Wood Surfaces: Patch nail holes, cracks and imperfections with exterior spackling compound. Sand and wipe clean. Woods subject to tannin bleeding should be primed with a stain blocking primer.

New Galvanized/Aluminum Metal Surfaces: Solvent wipe to remove surface contamination, then use an etching solution or abrade the surface by sanding.

Weathered Galvanized/Aluminum Surfaces: Power or hand wash with detergent and rinse thoroughly. The surface must be dull and slightly rough; use an etching solution or sand if needed.

Vinyl Surfaces: Power or hand wash with detergent and rinse thoroughly. All chalk residue must be removed from the surface.

Cement Board: Be sure surface is clean and free of all contaminants.

Ferrous Metal Surfaces: Remove loose rust and mill scale with hand or power abrading tools (reference SSPC-SP-2 or SSPC-SP-3).

Previously Painted Surfaces

- Power or hand washing is recommended to remove contamination. If oil or grease is present, use of a cleaner/degreaser is required. All cleaning residue must be completely rinsed from the surface. Allow to dry.
- Remove all loose coatings, deteriorated wood fibres and corrosion by scraping, sanding or other abrading method. Dull glossy, slick and/or non-porous surfaces with sandpaper.
- Patch and fill areas as needed. Spot prime bare areas with appropriate primer.

Mildew

Remove by using a solution of one (1) part household bleach and three (3) parts water. Apply to mildewed area and scrub. Allow solution to remain on the surface for 3 to 5 minutes then rinse completely and allow to dry before coating application.

APPLICATION

- Stir material prior to application. Intermix tinted containers to ensure color uniformity of all material.
- Equipment must be clean prior to start. Flush airless lines with water.
- Apply by brush, roller or spray. A good quality synthetic brush will make application easier. Select a roller cover suited for the texture of the surface to be coated. Airless tip sizes of .015 to .017 are recommended.
- Apply the product in full even coats and maintain a wet edge. Allow the product to dry between coats.
- Do not thin

ENVIRONMENTAL VARIABLES

Protect product from freezing prior to and during application. Minimum surface and air temperature required for application is 50° F (10° C) and at least 5° F (3° C) above the dew point. Curing is affected by temperature, humidity and air movement. The minimums must be maintained for at least eight (8) hours in order to achieve proper film formation. Application at elevated temperatures, wind conditions, and/or low humidity may require special application procedures to achieve proper film formation.

CLEAN-UP

Clean up spills immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment.

CAUTIONS

For exterior use only
Do not apply below 50° F
Protect from freezing
Not intended for use on floors
Do not take internally
Use with adequate ventilation
KEEP OUT OF REACH OF CHILDREN

*WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and wet mop. Before you start, find out how to protect yourself and your family by contacting the national Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Limited Warranty

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products. Since Diamond Vogel Paints does not control the application of its products, or the condition of the surfaces to which they are applied, Diamond Vogel Paint's liability will under no circumstances exceed replacement of the product.