



BS-Series
All Season
Exterior 100% Acrylic Latex Satin

Product Data Sheet

PRODUCT DESCRIPTION

All Season is high quality exterior 100% acrylic latex paint that dries to a soft satin finish. It's excellent fade resistance allows colors to remain beautiful for years and provides excellent durability on a variety of surfaces. All Season may be applied when surface and air temperature is at or above 35° F (2° C) and at least 5° F (3° C) above the dew point for a minimum of 8 hours. After that, lower temperatures can be tolerated.

TYPICAL USES

Formulated for use on residential and commercial exterior new or previously painted wood, hardboard, vinyl siding, cement board, aluminum, galvanized metal and masonry surfaces. Ideal for use on siding, gutters, soffits and foundations.

BASES & COLORS (tintable with ACS colorant)

BS-1575 Tintable White 0-6 oz/gal
BS-1576 Dark Base 4-10 oz/gal

PHYSICAL PROPERTIES (BS-1575)

Resin Type 100% Acrylic Latex
Clean-up Solvent Water
Finish 30 – 35 @ 85°
Solids by Weight 49 %
Solids by Volume 34 %

Recommended Dry Film
Thickness per Coat 2 – 3 mils

Wet Film to Achieve DFT 6 – 9 mils

Theoretical Coverage
@ 1 mil 545 ft²/gallon

Practical Coverage at
Recommended DFT¹ 182 – 273 ft²/gallon

Dry Times²
@ 70° F (21° C)
and 50% R.H. Touch ½ to 2 hours
 Recoat 2 to 4 hours

VOC's 96 grams/liter
(Range from 94 to 96 depending on color and base)

¹ Spread rates are estimates based on products volume solids and make no allowance for material loss during application. Actual spread rates may vary dependent on applicator experience, surface porosity and texture.

² Dry times may vary depending upon temperature, humidity and degree of air movement.

SPECIFICATIONS

Galvanized and Aluminum Metal

1 ct V-Cote 200 Acrylic Maintenance Primer
2 cts All Season Satin

Exterior Wood

1 ct AU-Series Alkyd Primer
or
1 ct BU-Series Acrylic Primer
2 cts All Season Satin

Ferrous Metal

1 ct AZ-Series Cote-All Universal Primer
2 cts All Season Satin

Block

Smooth
1 ct MC-0521 Masonry Conditioner
or
1 ct BU-Series Acrylic Latex Primer
2 cts All Season Satin

Porous

1 ct BF-Series Exterior Block Filler
2 cts All Season Satin

Poured Concrete

1 ct BU-Series Acrylic Latex Primer
2 cts All Season Satin

Cement Siding

Pre-primed
2 cts All Season Satin
Unprimed
1 ct BU-Series Acrylic Latex Primer
2 cts All Season Satin

Vinyl Siding

2 cts All Season Satin

For more detailed recommendations, please contact your local Diamond Vogel Sales Representative.

SURFACE PREPARATION

All surfaces must be cured, clean, sound, dry and free of all dirt, dust, efflorescence, wax, oil, grease, chalk and any other contamination that would interfere with new coating adhesion. **Bare surfaces must be properly prepared and primed prior to application of this product.**

Masonry Surfaces- Poured Concrete, Concrete Block:

New concrete and mortar should cure for a *minimum* of 30 days at 72° F (22° C) prior to coating application. Level all surface projections and mortar spatters by stoning. Rake mortar joints clean and remove all soluble salts.

Wood Surfaces: Patch nail holes, cracks and imperfections with exterior spackling compound. Sand and wipe clean. Woods subject to tannin bleeding should be primed with a stain blocking primer.

New Galvanized/Aluminum Metal Surfaces: Solvent wipe to remove surface contamination, then use an etching solution or abrade the surface by sanding.

Weathered Galvanized/Aluminum Surfaces: Power or hand wash with detergent and rinse thoroughly. The surface must be dull and slightly rough; use an etching solution or sand if needed.

Vinyl Surfaces: Power or hand wash with detergent and rinse thoroughly. All chalk residue must be removed from the surface.

Cement Board: Be sure surface is clean and free of all contaminants.

Ferrous Metal Surfaces: Remove loose rust and mill scale with hand or power abrading tools (reference SSPC-SP-2 or SSPC-SP-3).

Previously Painted Surfaces

- Power or hand washing is recommended to remove contamination. If oil or grease is present, use of a cleaner/degreaser is required. All cleaning residue must be completely rinsed from the surface. Allow to dry.
- Remove all loose coatings, deteriorated wood fibers and corrosion by scraping, sanding or other abrading method. Dull glossy, slick and/or non-porous surfaces with sandpaper.
- Patch and fill areas as needed. Spot prime bare areas with appropriate primer.

Mildew

Remove by using a solution of one (1) part household bleach and three (3) parts water. Apply to mildewed area and scrub. Allow solution to remain on the surface for 3 to 5 minutes then rinse completely and allow to dry before coating application. Do not add detergents or ammonia to the bleach/water solution.

APPLICATION

- Stir material prior to application. Intermix tinted containers to ensure color uniformity of all material.
- Equipment must be clean prior to start. Flush airless lines with water.
- Apply by brush, roller or spray. A good quality synthetic brush will make application easier. Select a roller cover suited for the texture of the surface to be coated. Airless tip sizes of .015 to .017 are recommended.
- Apply the product in full even coats and maintain a wet edge. Allow the product to dry between coats.
- Do not thin

ENVIRONMENTAL VARIABLES

Protect product from freezing prior to and during application. Minimum surface and air temperature required for application is 35° F (2° C) and at least 5° F (3° C) above the dew point. Curing is affected by temperature, humidity and air movement. The minimums must be maintained for at least eight (8) hours in order to achieve proper film formation. Application at elevated temperatures, wind conditions, and/or low humidity may require special application procedures to achieve proper film formation.

CLEAN-UP

Clean up spills immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment.

CAUTIONS

For exterior use only
Do not apply below 35° F
Protect from freezing
Not intended for use on floors
Do not take internally
Use with adequate ventilation
KEEP OUT OF REACH OF CHILDREN

*WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and wet mop. Before you start, find out how to protect yourself and your family by contacting the national Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Limited Warranty

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products. Since Diamond Vogel Paints does not control the application of its products, or the condition of the surfaces to which they are applied, Diamond Vogel Paint's liability will under no circumstances exceed replacement of the product.