



Acryl Prime Interior 100% Acrylic Primer/Sealer

Product Data Sheet

PRODUCT DESCRIPTION

Acryl Prime is a premium quality 100% acrylic interior latex primer/sealer that offers excellent hold out for both latex and oil topcoats. It also has better alkaline resistance than conventional vinyl acrylic primers.

TYPICAL USES

Formulated for use on residential or commercial surfaces of wood, plaster, drywall, brick, cement block and masonry.

BASES & COLORS (tintable with ACS colorant)

DU-1502 White 0-4 oz/gal

With the addition of ACS colorant, it can be shaded to approximate the color of the finish coat.

PHYSICAL PROPERTIES (DU-1502)

Resin Type 100% Acrylic

Clean-up Solvent Water

Finish 5 – 10 @ 85°

Solids by Weight 47 %

Solids by Volume 34 %

Recommended Dry Film
Thickness per Coat 1.5 – 2 mils

Wet Film to Achieve DFT 4.5 – 6 mils

Theoretical Coverage
@ 1 mil 545 ft²/gallon

Practical Coverage at
Recommended DFT¹ 272 – 363 ft²/gallon

Dry Times²
@ 70° F (21° C)
and 50% R.H. Touch 1 hour
Recoat 4 hours

VOC's 150 grams/liter

1 Spread rates are estimates based on products volume solids and make no allowance for material loss during application. Actual spread rates may vary dependent on applicator experience, surface porosity and texture.

2 Dry times may vary depending upon temperature, humidity and degree of air movement.

SPECIFICATIONS

Interior Wood

1 ct Acryl Prime
2 cts Any Diamond Vogel Interior Latex, Alkyd or Waterborne Epoxy finish.

Interior Plaster

1 ct Acryl Prime
2 cts Any Diamond Vogel Interior Latex, Alkyd or Waterborne Epoxy finish.

Interior Masonry Surfaces

1 ct Acryl Prime
2 cts Any Diamond Vogel Interior Latex, Alkyd or Waterborne Epoxy finish.

For more detailed recommendations, please contact your local Diamond Vogel Sales Representative.

SURFACE PREPARATION

All surfaces must be cured, clean, sound, dry and free of all dirt, dust, efflorescence, wax, oil, grease, chalk and any other contamination that would interfere with new coating adhesion. **Bare surfaces must be properly prepared prior to application of this product.**

Masonry Surfaces - Poured Concrete, Concrete Block:

New concrete and mortar should cure for a *minimum* of 30 days at 72° F (22° C) prior to coating application. Level all surface projections and mortar spatters by stoning. Rake mortar joints clean and remove all soluble salts.

Wood Surfaces: Patch nail holes, cracks and imperfections with exterior spackling compound. Sand and wipe clean. Woods subject to tannin bleeding should be primed with a stain blocking primer.

Plaster Surfaces: New Plaster must cure for a minimum of 30 days at 72° F (22° C) prior to coating application. Sand smooth and dust. Fill cracks with spackling compound, allow to dry and sand smooth. Remove sanding dust.

Drywall Surfaces: Fill nail holes and imperfections with spackling compound and allow to dry. Sand tape joints and spackled areas and remove dust.

Previously Painted Surfaces

- Cleaning is recommended to remove contamination. If oil or grease is present, use of a cleaner/degreaser is required. All cleaning residue must be completely rinsed from the surface. Allow to dry.
- Remove all loose coatings and corrosion by scraping, sanding or other abrading method. Dull glossy, slick and/or non-porous surfaces with sandpaper.
- Patch and fill areas as needed. Spot prime bare areas with appropriate primer.

Mildew

Remove by using a solution of one (1) part household bleach and three (3) parts water. Apply to mildewed area and scrub. Allow solution to remain on the surface for 3 to 5 minutes then rinse completely and allow to dry before coating application. Do not add detergents or ammonia to the bleach/water solution.

APPLICATION

- Stir material prior to application. Intermix tinted containers to ensure color uniformity of all material.
- Equipment must be clean prior to start. Flush airless lines with clean water.
- Apply by brush, roller or spray. A good quality synthetic brush will make application easier. Select a roller cover suited for the texture of the surface to be coated. Airless tip sizes of .015 to .019 are recommended.
- Apply the product in full even coats and maintain a wet edge. Allow the product to dry between coats.
- Do not thin.

ENVIRONMENTAL VARIABLES

Protect product from freezing prior to and during application. Minimum surface and air temperature required for application is 50° F (10° C) and at least 5° F (3° C) above the dew point. Curing is affected by temperature, humidity and air movement; cold temperatures will greatly increase the dry time. Application at elevated temperatures, wind conditions, and/or low humidity may require special application procedures to achieve proper film formation.

CLEAN-UP

Clean up spills immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment.

CAUTIONS

For interior use only
Do not apply below 50° F
Not intended for use on floors
Protect from freezing
Do not take internally
Use with adequate ventilation
KEEP OUT OF REACH OF CHILDREN

***WARNING!** If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and wet mop. Before you start, find out how to protect yourself and your family by contacting the national Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Limited Warranty

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products. Since Diamond Vogel Paints does not control the application of its products, or the condition of the surfaces to which they are applied, Diamond Vogel Paint's liability will under no circumstances exceed replacement of the product.