

PermAcryl

EXTERIOR

PermAcryl is a premium quality exterior 100% acrylic latex that dries to a durable finish. The 100% acrylic technology provides excellent fade resistance which allows colors to remain beautiful for years.

Features:

- 100% Acrylic
- Available in: White, Midtone, Deep and Neutral Bases and Ready Mixed Colors
- Flat, Satin and Semi-Gloss Finishes
- Low Temp Application down to 35° Flat, Satin



For more information call:

DV Representative
() -

Diamond Vogel
1-800-72VOGEL
www.diamondvogel.com

Formulated for use on residential and commercial exterior, new or previously painted, wood, hardboard, vinyl siding, cement board, aluminum, galvanized metal and masonry surfaces. It is ideal for use on siding, gutters, soffits and foundations.

PermAcryl Exterior

Surface Preparation

Physical Properties

All surfaces must be cured, clean sound, dry and free of all dirt, dust, efflorescence, wax, oil grease, chalk and any other contamination that would interfere with the new coating adhesion. **Bare surfaces must be properly prepared and primed prior to application of this product.**

Previously Painted Surfaces

Power or hand washing is recommended to remove contamination. If oil or grease is present, the use of a cleaner/degreaser is required. All cleaning residue must be completely rinsed from the surface. Allow to dry. Remove all loose coatings and corrosion by scraping, sanding or other abrading method. Dull glossy, slick and/or non-porous surfaces with sandpaper. Patch and fill areas as needed. Spot prime bare areas with appropriate primer.

Mildew

Remove by using a solution of one (1) part household bleach and three (3) parts water. Apply to mildewed area and scrub. Allow solution to remain on the surface for 3 to 5 minutes then rinse completely and allow to dry before coating application.

PHYSICAL PROPERTIES(BA-1501)

Resin Type 100% Acrylic Latex
 Clean-up Solvent Water
 Finish 5-10 @ 85°
 Solids by Weight 52 %
 Solids by Volume 40 %

Recommended Dry Film Thickness per Coat 1.5 – 2 mils
 Wet Film to Achieve DFT 4 – 5 mils

Theoretical Coverage @ 1 mil 641 ft²/gallon

Practical Coverage at Recommended DFT 320 – 427 ft²/gallon

Dry Times

@ >50° F (10° C) Touch ½ to 2 hours Recoat 2 to 4 hours
 @ 35° F to 49° F Touch 2 to 4 hours Recoat 24 hours

	Flat	Satin	Semi-Gloss
VOC's	94-98 g/L	96-98 g/L	120-139 g/L
(Range from 94-139 depending on color and base)			

System Recommendation

<u>Substrate</u>	<u>Primer</u>	<u>Finish</u>
Exterior Wood	BU-1501 Sure Grip Primer BU-1510 Weather-Plate Primer AU-1404 Prime-O-Seal AU-1301 Flat Oil Primer	BA/BS or BN Series Permacyrl Ext.
Ferrous Metal	AZ- CoteAll Primers V-Cote 200 Acrylic Maintenance Primer (MC-Series)	BA/BS or BN Series Permacyrl Ext.
Galvanized Metal/ Aluminum	V-Cote 200 Acrylic Maintenance Primer (MC-Series)	BA/BS or BN Series Permacyrl Ext.
Cement Siding	Pre-Primed 2 cts Weather Plate BF/BS Un-Primed 1 ct BU-Series Acrylic Prime	BA/BS or BN Series Permacyrl Ext.
Smooth Block	MC-0521 Surface Conditioner	BA/BS or BN Series Permacyrl Ext.
Porous Block	BF-1504 Fil-Kote Block Filler BF-1501 Permafil Block Filler	BA/BS or BN Series Permacyrl Ext.
Poured Concrete	BU-1501 Sure Grip Primer BU-1510 Weather-Plate Primer	BA/BS or BN Series Permacyrl Ext.
Vinyl	Self Priming	BA/BS or BN Series Permacyrl Ext.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.



www.diamondvogel.com
 1-800-72VOGEL (728-6435)

The contents of this literature are for informational purposes only. Consult the product data sheet for complete information.