

# Paramount

Superior Exterior Coating

**Paramount is a premium quality exterior 100% acrylic latex that dries to a durable finish. Enhanced brush and roll characteristics provide unsurpassed application properties.**

## Features:

- 100% Acrylic
- Available in:  
White, Midtone, Deep  
and Neutral Bases,
- Available in Matte Flat  
and Satin Finishes
- Low Temp Application  
down to 35°



For more information call:

DV Representative  
( ) -

Diamond Vogel  
1-800-72VOGEL  
[www.diamondvogel.com](http://www.diamondvogel.com)

Formulated for use on residential and commercial exterior new or previously painted wood, hardboard, vinyl siding, cement board, aluminum, and galvanized metal and masonry surfaces. Ideal for use on siding, gutters, soffits and foundations.

Paramount Superior Exterior Coating

# Surface Preparation

# Physical Properties

All surfaces must be cured, clean, sound, dry and free of all dirt, dust, efflorescence, wax, oil, grease, chalk and any other contamination that would interfere with the new coating adhesion. **Bare surfaces must be properly prepared prior to application of this product.**

### Previously Painted Surfaces

Power or hand washing is recommended to remove contamination. If oil or grease is present, the use of a cleaner/degreaser is required. All cleaning residue must be completely rinsed from the surface. Allow to dry.

Remove all loose coatings and corrosion by scraping, sanding or other abrading method. Dull glossy, slick and/or non-porous surfaces with sandpaper. Patch and fill areas as needed. Spot prime bare areas with appropriate primer.

### Mildew

Remove by using a solution of one (1) part household bleach and three (3) parts water. Apply to mildewed area and scrub. Allow solution to remain on the surface for 3 to 5 minutes then rinse completely and allow to dry before coating application.

### PHYSICAL PROPERTIES(BF-1560)

Resin Type 100% Acrylic Latex  
 Clean-up Solvent Water  
 Finish 0-5 @ 85°  
 Solids by Weight 52 %  
 Solids by Volume 35 %

Recommended Dry Film Thickness per Coat 1.5 – 2 mils  
 Wet Film to Achieve DFT 4 – 5 mils

Theoretical Coverage @ 1 mil 561 ft<sup>2</sup>/gallon

Practical Coverage at Recommended DFT<sup>1</sup> 280 - 374 ft<sup>2</sup>/gallon

### Dry Times

@ >50° F (10° C) Touch ½ to 2 hours Recoat 2 to 4 hours  
 @ 35° F to 49° F Touch 2 to 4 hours Recoat 24 hours

VOC's Flat 97 g/L Satin 115-125 g/L  
 (Range from 97-125 depending on color and base)

# System Recommendation

<u>Substrate</u>	<u>Primer</u>	<u>Finish</u>
Exterior Wood	BU-Series Acrylic Primer AU-Series Alkyd Primer	BF/BS-Series Paramount Exterior
Cement Siding	BU-Series Acrylic Primer Self Priming	BF/BS-Series Paramount Exterior
Vinyl Siding	Self Priming	BF/BS-Series Paramount Exterior
Galvanized & Aluminum	V-Cote 200 Acrylic Maintenance Primer (MC-Series)	BF/BS-Series Paramount Exterior
Poured Concrete	BU-Series Acrylic Primer	BF/BS-Series Paramount Exterior
Ferrous Metal	AZ-Series Cote-All Primers V-Cote 200 Acrylic Maintenance Primer (MC-Series)	BF/BS-Series Paramount Exterior
Exterior Block (Smooth)	MC-0521 Masonry Conditioner BU-Series Acrylic Primer	BF/BS-Series Paramount Exterior
Exterior Block (Porous)	BF-Series Exterior Block Filler	BF/BS-Series Paramount Exterior

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).



www.diamondvogel.com  
 1-800-72VOGEL (728-6435)

The contents of this literature are for informational purposes only. Consult the product data sheet for complete information.