

SATINAMEL

Satinamel is a premium quality interior/exterior alkyd enamel that dries to a durable soft satin finish. Satinamel may be used on a wide variety of substrates where a long lasting, durable finish is required.

Features:

- Low Odor
- Excellent Application Characteristics
- Soft Satin Finish
- Tintable to all Showcase Formulations
- Yellows less than typical alkyd finishes



For more information call:

DV Representative
() -

Diamond Vogel
1-800-72VOGEL
www.diamondvogel.com

Satinamel is formulated for use as a finish coat on primed or previously painted interior or exterior residential or commercial surfaces. Satinamel is ideal for surfaces such as woodwork, drywall, doors, trim and metal surfaces.

Satinamel Interior/Exterior Alkyd

Surface Preparation

Physical Properties

All surfaces must be cured, clean, sound, dry and free of all dirt, dust, efflorescence, wax, oil, grease, chalk and any other contamination that would interfere with new coating adhesion. **Bare surfaces must be properly prepared and primed prior to application of this product.**

Previously Painted Surfaces

Power or hand washing is recommended to remove contamination. If oil or grease is present, use of a cleaner/degreaser is required. All cleaning residue must be completely rinsed from the surface. Allow to dry. Remove all loose coatings and corrosion by scraping, sanding or other abrading method. Dull glossy, slick and/or non-porous surfaces with sandpaper. Patch and fill areas as needed. Spot prime bare areas with appropriate primer.

Mildew

Remove by using a solution of one (1) part household bleach and three (3) parts water. Apply to mildewed area and scrub. Allow solution to remain on the surface for 3 to 5 minutes then rinse completely and allow to dry before coating application. Do not add detergents or ammonia to the bleach/water solution.

PHYSICAL PROPERTIES(CS-1331)

Resin Type	Alkyd
Clean-up Solvent	Do not thin
Finish	35-40 @ 60°
Solids by Weight	75 %
Solids by Volume	55 %
Recommended Dry Film Thickness per Coat	1.5 - 2 mils
Wet Film to Achieve DFT	3 - 4 mils
Theoretical Coverage @ 1 mil	882 ft ² /gallon
Practical Coverage at Recommended DFT ¹	441 - 588 ft ² /gallon
<u>Dry Times</u> ² @ 70° F (21° C) and 50% R.H.	Touch 4 hours Recoat 12 hours
VOC's (Range from 345 to 380 g/L depending on base)	345 grams/liter

System Recommendation

<u>Substrate</u>	<u>Primer</u>	<u>Finish</u>
Interior Wood	DU-1508 Latex Enamel Undercoat CU-1401 Alkyd Enamel Undercoat	Satinamel
Drywall	DU-Series Primer/Sealers	Satinamel
Plaster	CU-1401 Alkyd Enamel Undercoat DU-1502 100% Acrylic Primer/Sealer	Satinamel
Interior Smooth Block	DU-1502 100% Acrylic Primer/Sealer	Satinamel
Poured Concrete	DU-1502 Interior Primer/Sealer BU-1510 Weather-Plate Primer	Satinamel
Ferrous Metal	AZ-Series Cote-All Primers V-Cote 200 Acrylic Maintenance Primer (MC-Series)	Satinamel
Exterior Concrete Block	V-Cote 200 Acrylic Maintenance Primer (MC-Series) BF-1501 Permafil Acrylic Block Filler	Satinamel
Galvanized & Aluminum	V-Cote 200 Acrylic Maintenance Primer (MC-Series)	Satinamel

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.



www.diamondvogel.com
1-800-72VOGEL (728-6435)

The contents of this literature are for informational purposes only. Consult the product data sheet for complete information.